

SoftCoat[®] RP

Non-Structural Repair Mortar

SoftCoat RP is a Portland cement-based product that is non-shrinkage and has high strength. The aforementioned product is used to repair obsolete and honeycombed concrete and cement substrates. Also, this product has a cosmetic form due to its high consistency and bonding.

This product meets the requirements of grade R2 of the non-structural category of the EN 1504-3 Standard. Also, the physical and chemical properties of the SoftCoat RP are produced according to the following table:

Physical State	Powder
Color	Grey
Bulk Specific Weight of the Powder	1/42 ± 0/02 g/cm3
The Specific Weight of ready-to-use Mortar	1/91 ± 0/02 g/cm3
Chloride Content	Little

The usage and effect of the surface repair

The usage of the repair

- Repairing the honeycombed and destroyed surfaces of the concrete
- Filling the pores of the concrete surface
- Subgrade the surface to implement surface waterproofing.

The advantages of using the surface repair

- It has high strength and bonding to concrete surfaces.
- Non-shrinkage
- High durability
- It leads to a reduction in the permeability of water
- It is a single-component and easy to use.
- Chloride ion-free

The instruction to use the surface repair

The allowable range and instruction to use the repair material

- The desired surface should be cleaned from any weakness with suitable tools, and grooves must be made in different directions to more than 2 mm depth within a suitable distance to involve the paste in the surface texture completely.
- 4.5 liters of water is poured into the mixer per 25 kg packet of SoftCoat RP, and the powder is added to the water at a suitable rate. The mixing should continue so that a uniform mortar is obtained.
- After surface cleaning, a primer can be used for subgrade to increase bonding. The CapcoBond MO40 is suitable for this purpose. This primer waterproofs the surface as well as increases the bonding. The prepared paste must be applied by trowel on the surface before the primer dries completely.
- For repairs with more than 3 cm depth, an amount of sand proportionate to the concrete surface being repaired must be mixed with the product. The size of the sands is 3 to 10 mm depending on the repair surface. Also, the used sand must be washed and cleaned. It is necessary to use CapcoBond MO40 for bedding.

Curing: The surface will reach full setting about 3 to 4 hours after troweling. It is necessary to use the wet curing method for the repaired surface for at least 72 hours.



Safety tips for using the surface repair

This product is based on Portland cement which is highly alkaline and is dangerous in contact with the skin. Therefore, it is necessary to use a suitable gown, goggles, and mask while working. It is also necessary to take the following tips into consideration:

- Blink in water for at least 15 minutes in case of eye contact
- Wash your skin with clean water for 15 minutes in case of any contact with the skin
- The contaminated clothes must be washed with suitable detergents to be usable for further work.
- It is necessary to visit a doctor if the injured individual still feels uncomfortable

Other necessary notes for using the surface repair

The corrosion of the product

This product does not start or extend corrosion in the buried bars in concrete, the pre-stressed steel, floor systems, and the roof made of galvanized steel. No Calcium chloride or any other compounds containing chloride is used in producing the SoftCoat RP.

Transportation and storage of the product

The conditions and maintenance temperature of transportation

The allowable transportation and maintenance temperature of this product is between 5 and 35 °C. It is also necessary to consider the following tips:

- Avoid putting the container having the admixture in direct exposure to sunlight
- Avoid putting the product in direct exposure to moisture.

The lifetime of the product

If the containers of this product are conserved and stored in a standard condition, they will be usable for 12 months.

The packaging

This product is supplied in 25 Kg packets.

Complementary information

Contact the technical section of Capco Company for complementary information. You can also refer to the performance form of (SoftCoat RP-PPI) RP for more information on the performance of this product.