

CapcoSet® AS

Accelerating Admixture

CapcoSet AS is an Accelerating Admixture to speed up the setting time of the grouts and mortars. This admixture is chloride-ion free and does not lead to corrosion of the bars and steel surfaces.

This product is produced based on the general requirements of Table 1 and the performance requirements of the Iran National Standard No. 2930-5. Also, this admixture meets the requirements of the EN 934-5 standard.

The physical and chemical properties of CapcoSet AS are according to the following table and produced in the allowable changing range of Iran National Standard No.2930-5.

(The previous name of this product was Plastit AS)

Physical State	Gel Liquid
Color	Colorless
Density	1/3 ± 0/02 g/cm3
Chloride Content	Little
The equivalent	Little
рН	$\textbf{7} \pm \textbf{1}$
Freezing Temperature	-5°C

The usage and the effect of the admixture on the concrete

The usage of the admixture

- The production and implementation of the mortars with fast setting time
- The implementation of the spray mortar
- Grouting

The advantages of using the admixture in concrete

- Accelerating the initial and final setting time of the cement paste
- Increasing the compressive strength of the concrete at early ages

The effect of the admixture on fresh concrete

- It reduces the initial and final setting time of the standard mortar depending on the amount used
- The production of air bubbles in the fresh concrete is controlled in a way that the changes in the air percentage remain in the allowable standard range announced in the properties sheet.

The effect of the admixture on the hardened concrete

- It increases the initial strength of the concrete in an equal water-to-cement ratio
- It does not reduce the 28-day strength of the concrete in an equal water-to-cement ratio and air bubble percentage

The instruction to use the admixture in the concrete

The allowable range of using the admixture in the concrete

The allowable range for using The CapcoSet AS is from 2% to 10% of the cement content (2 to 10 kg per 100 kg of cement material weight including cement, silica fume, slag, fly ash, and other similar pozzolans). The temperature at the time of concrete casting and after that, the concrete mix design, the thickness, and the volume of the concrete section are the main indices to determine this admixture. Specifying the optimum amount of this admixture is accomplished bγ considering the aforementioned indices and the required test in the laboratory.



The instructions to add admixture to concrete

To use the admixture, it is necessary to dilute the admixture with water twice the volume of the admixture It is also necessary to take the following notes into consideration:

- Mix the concrete for 2 to 5 minutes after adding the admixture and assure the uniform distribution of the admixture in the mortar or grout.
- Avoid the direct contact of the admixture with the dry cement and aggregates

Safety tips while using the admixture

This product is categorized as a dangerous substance; and it can be allergic to contact with skin. Therefore, it is necessary to use a suitable gown, goggles, and mask while working and take the following tips into consideration:

- Blink in water for at least 15 minutes in case of eye contact
- Wash your skin with clean water for 15 minutes in case of any contact with the skin
- The contaminated clothes must be washed with suitable detergents to be usable for further work.
- It is necessary to visit a doctor if the injured individual still feels uncomfortable

Other necessary notes in using the admixtures

Compatibility of admixture with other products

This admixture is used to accelerate the setting time of the mortar and grout. To use other admixtures with this product it is necessary to consult the technical section of Capco Company and carry out the required tests.

The corrosion of admixture

This product does not start or extend corrosion in the buried bars in concrete, the pre-stressed steel, floor systems, and the roof made of galvanized steel. No Calcium chloride or any other compounds containing chloride is used in producing the CapcoSet AS.

Transportation and storage of the admixture substance

The conditions and maintenance temperature of transportation

The allowable transportation and maintenance temperature of this product is between 5 and 25 °C. It is also necessary to consider the following tips:

- Avoid putting the container having the admixture in direct exposure to sunlight
- Prevent the admixture from freezing

The admixture lifetime

If the containers of this product are conserved and stored in a standard condition, they will be usable for 12 months.

The admixture substance packaging

This product is supplied in 24 Kg gallons, 240 Kg barrels, and 1100 Kg Pallets.

Complementary information

Contact the technical section of Capco Company for complementary information. You can also refer to the performance form of (CapcoSet AS-PPI) AS for more information on the performance of this product and its efficiency in the characteristics of fresh and hardened concrete.